

Certificate of Analysis-Brown Fused Alumina

General Information

Product	: Brown Fused Alumina for Resin Bonded Abrasives,
Apply to	:Vitrified Bonded Abrasives, Sandblasting, Polishing,
Surface Preparation	
Other Names	: Brown Fused Aluminium Oxide, Brown Aluminum Oxide,
Brown Corundum	
Country of Origin	: China
Manufacturer of Material	: Komeno(Beijing)International Trading Co.,Ltd.
Features	: Clean Material, Good Chemical Content, Good Shape
Picture of Product:	



Physical Specifications & Package

Main Content	: Al ₂ O ₃ (Aluminum Oxide)
Specific Gravity	: $\cong 3.90$ g /cm ³
Bulk Density	: 1.4-2.3 kg / m ³
Hardness	: 9 MOSH
Color	: Brown
Melting Point	: 2300℃
Sizes Available	: F8-F220, F280-F2000, other sizes to request
Package	: Jumbo Bag, 25kg Bag and 40 Bags on a Pallet



Komeno(Beijing)International Trading Co.,Ltd.

No.111 Yuquanying,Fengtai District, Beijing City,Beijing,100071,P.R.CHINA

TEL: 0086-10-83323238 EMAIL: Sales@komeno.com.cn

Particle Distribution & Chemical Content

Brown Fused Alumina FEPA Sizes for Bonded Abrasives and Blasting(Fixed Furnace)

Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F12	+2.80	+2.00	+1.70	+1.40	-1.18	AL ₂ O ₃	95.50%
	Standard	0%	0-20%	45-100%	70-100%	0-3%	SiO ₂	1.40%
	Sample 1	0	12	59	87	0.5	TiO ₂	2.39%
	Sample 2	0	12	59	87	0.5	Fe ₂ O ₃	0.17%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F14	+2.36	+1.70	+1.40	+1.18	-1.00	AL ₂ O ₃	95.30%
	Standard	0%	0-20%	45-100%	70-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	5	62	91	0.5	TiO ₂	2.33%
	Sample 2	0	5	62	91	0.5	Fe ₂ O ₃	0.14%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F16	+2.00	+1.40	+1.18	+1.00	-0.85	AL ₂ O ₃	95.45%
	Standard	0%	0-20%	45-100%	70-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	5	52	81	0.5	TiO ₂	2.33%
	Sample 2	0	5	52	81	0.5	Fe ₂ O ₃	0.14%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F20	+1.70	+1.18	+1.00	+0.85	-0.710	AL ₂ O ₃	95.34%
	Standard	0%	0-20%	45-100%	70-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	8	56	88	0.5	TiO ₂	2.38%
	Sample 2	0	8	56	88	0.5	Fe ₂ O ₃	0.18%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F22	+1.40	+1.00	+0.85	+0.710	-0.600	AL ₂ O ₃	95.37%
	Standard	0%	0-20%	45-100%	70-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	7	51	82	0.5	TiO ₂	2.30%
	Sample 2	0	7	51	82	0.5	Fe ₂ O ₃	0.15%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F24	+1.18	+0.85	+0.71	+0.60	-0.50	AL ₂ O ₃	95.27%
	Standard	0%	0-25%	45-100%	65-100%	0-3%	SiO ₂	1.38%
	Sample 1	0	15	53	82	0.5	TiO ₂	2.34%
	Sample 2	0	15	53	82	0.5	Fe ₂ O ₃	0.14%



Komeno(Beijing)International Trading Co.,Ltd.

No.111 Yuquanying,Fengtai District, Beijing City,Beijing,100071,P.R.CHINA TEL:
0086-10-83323238 EMAIL: Sales@komeno.com.cn

Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F30	+1.00	+0.71	+0.60	+0.50	-0.425	AL ₂ O ₃	95.22%
	Standard	0%	0-25%	45-100%	65-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	16	57	76	0.5	TiO ₂	2.21%
	Sample 2	0	15	57	75	0.5	Fe ₂ O ₃	0.20%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F36	+0.85	+0.60	+0.50	+0.425	-0.355	AL ₂ O ₃	95.33%
	Standard	0%	0-25%	45-100%	65-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	6	50	88	0.5	TiO ₂	2.35%
	Sample 2	0	6	50	88	0.5	Fe ₂ O ₃	0.16%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F40	+0.710	+0.500	+0.425	+0.355	-0.300	AL ₂ O ₃	95.20%
	Standard	0%	0-30%	40-100%	65-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	5	53	82	0.5	TiO ₂	2.29%
	Sample 2	0	5	53	82	0.5	Fe ₂ O ₃	0.14%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F46	+0.60	+0.425	+0.355	+0.300	-0.250	AL ₂ O ₃	95.30%
	Standard	0%	0-30%	40-100%	65-100%	0-3%	SiO ₂	1.37%
	Sample 1	0	4	45	85	0.5	TiO ₂	2.29%
	Sample 2	0	4	45	85	0.5	Fe ₂ O ₃	0.17%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F60	+0.425	+0.30	+0.25	+0.212	-0.18	AL ₂ O ₃	95.25%
	Standard	0%	0-30%	40-100%	65-100%	0-3%	SiO ₂	1.37%
	Sample 1	0	12	53	83	1.0	TiO ₂	2.28%
	Sample 2	0	12	53	83	1.0	Fe ₂ O ₃	0.15%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F70	+0.355	+0.250	+0.212	+0.180	-0.150	AL ₂ O ₃	95.18%
	Standard	0%	0-25%	40-100%	65-100%	0-3%	SiO ₂	1.39%
	Sample 1	0	17	52	80	0.5	TiO ₂	2.30%
	Sample 2	0	17	52	80	0.5	Fe ₂ O ₃	0.12%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F80	+0.300	+0.212	+0.180	+0.150	-0.125	AL ₂ O ₃	95.24%
	Standard	0%	0-25%	40-100%	65-100%	0-3%	SiO ₂	1.40%



Komeno
Grinding & Polishing Solutions

Komeno(Beijing)International Trading Co.,Ltd.

No.111 Yuquanying,Fengtai District, Beijing City,Beijing,100071,P.R.CHINA TEL:

0086-10-83323238 EMAIL: Sales@komeno.com.cn

	Sample 1	0	21	45	75	0.5	TiO ₂	2.35%
	Sample 2	0	21	45	75	0.5	Fe ₂ O ₃	0.18%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F90	+0.250	+0.180	+0.150	+0.125	-0.106	AL ₂ O ₃	95.06%
	Standard	0%	0-20%	40-100%	65-100%	0-3%	SiO ₂	1.33%
	Sample 1	0	9	52	87	0.5	TiO ₂	2.45%
	Sample 2	0	9	52	87	0.5	Fe ₂ O ₃	0.14%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F100	+0.212	+0.150	+0.125	+0.106	-0.075	AL ₂ O ₃	95.17%
	Standard	0%	0-20%	40-100%	65-100%	0-3%	SiO ₂	1.38%
	Sample 1	0	13	50	78	0.5	TiO ₂	2.31%
	Sample 2	0	13	50	78	0.5	Fe ₂ O ₃	0.15%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F120	+0.180	+0.125	+0.106	+0.090	-0.063	AL ₂ O ₃	95.01%
	Standard	0%	0-20%	40-100%	65-100%	0-3%	SiO ₂	1.40%
	Sample 1	0	4	50	87	0.5	TiO ₂	2.37%
	Sample 2	0	4	50	87	0.5	Fe ₂ O ₃	0.15%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F150	+0.150	+0.106	+0.075	+0.063	-0.045	AL ₂ O ₃	94.28%
	Standard	0%	0-15%	40-100%	65-100%	0-3%	SiO ₂	1.42%
	Sample 1	0	4	70	83	0.5	TiO ₂	2.39%
	Sample 2	0	4	70	83	0.5	Fe ₂ O ₃	0.16%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F180	+0.125	+0.090	+0.063	+0.053		AL ₂ O ₃	95.04%
	Standard	0%	0-15%	40-100%	65-100%		SiO ₂	1.39%
	Sample 1	0	7	50	76		TiO ₂	2.39%
	Sample 2	0	7	50	76		Fe ₂ O ₃	0.16%
Physical Analysis	Grit#	Max Size	Big Size	Basic Size	Mixed Size	Small Size	Chemical Analysis	
	F220	+0.106	+0.075	+0.053	+0.045		AL ₂ O ₃	94.81%
	Standard	0%	0-15%	40-100%	60-100%		SiO ₂	1.39%
	Sample 1	0	6	50	78		TiO ₂	2.45%
	Sample 2	0	6	50	78		Fe ₂ O ₃	0.16%

Tilting Furnace Material also Available

Shape Compare(Roller & Bamarc Crushed/Milled)



Bamarc Matetrial has higher Bulk Density better for abrasives.
